Bureau Veritas (India) Private Limited Construction Services Laboratory

A-8, Sector 6, Opp. Rohan Motors Noida - 201 301, Uttar Pradesh. INDIA

Tel.: +91 120 4770050

Email: lab.delhi@bureauveritas.com

TEST REPORT



Test Order/Report No: BVIPL: EPOXY GROUT/25951C/718/3/2024

Job ID No: 2024/Mar/2406867-(24009973)

Date of Issue: 24.05.2024 Date of Receipt: 07.03.2024

Page 1 of 1

Issued to: RACHTR CHEMICALS PRIVATE LIMITED

Plot No. GI-586, RIICO Industrial Area, Khuhkhera, Rajasthan-301707

TEST REPORT ON RACHTR FLOOR EP1010N'

Source of Sample*

RACHTR CHEMICALS PRIVATE LIMITED

No. of Sample Tested

: 1 (One)

Customer Reference*

Email Dated 07.03.2024

Project*

Not Furnished

Condition of Sample

Satisfactory (2 Lequied A,B and Power C)

Sample Drawn by

Sample Identification*

* 'Epoxy floor Top Coat Mixing retio (A:B:C=1.0:0.5:2.1)

Grade/Type*

: RACHTR FLOOR EP1010N

Brand*

: RACHTR

Period of Test

£ 25.04.2024 to 23.05.2024

Mechanical Testing-(Building Materials)-Epoxy Grout

S.No.	Tests	Results	Test Method
1.	Compressive Strength, N/mm ² 28 Days		
	1)	63.4	
	II)	60.7	BS-6319 (P-2)
	II)	61.9	
	Average	62.0	
2.	Flexural Strength, N/mm ² 28 Days		
	i)	25.8	
	II)	22.9	BS-6319 (P-3)
	11)	25.1	, ,
	Average	24.6	

****End of Report****





This page of the report is not under NABL accreditation

*Indicates information supplied by the customer for which the laboratory has no control. Sampling not done by laboratory, results relate to the sample tested only. The contents of the report shall not be reproduced either in full or in part without prior written consent of the issuing authority. All services are rendered in accordance with Bureau Veritas General conditions of service.

Kindly refer to the T&C at www.bureauveritas.co.in – General Terms & Conditions – General terms & Conditions-BVIL Regd. Office: 72, Business Park, Ground Floor, Marol Industrial Area, MIDC, Cross Road 'C', Andheri (East), Mumbai - 400 093, INDIA • www.bureauveritas.co.in

Bureau Veritas (India) Private Limited Construction Services Laboratory

A-8, Sector 6, Opp. Rohan Motors Noida - 201 301, Uttar Pradesh. INDIA

Tel.: +91 120 4770050

Email: lab.delhi@bureauveritas.com

TEST REPORT



Test Order/Report No: BVIPL: RACHTR FLOOR EP1010N/25951C/2301/3/2024

Date of Issue: 29.04.2024 Date of Receipt: 22.03.2024

Page 1 of 1

Job ID No: 2024/Mar/2408463-(UIN-24012224)

Issued to: RACHTR CHEMICALS PRIVATE LIMITED

Plot No. GI-586, RIICO Industrial Area, Khuhkhera, Rajasthan-301707

TEST REPORT ON RACHTR FLOOR EP1010N'

Source of Sample*

RACHTR CHEMICALS PRIVATE LIMITED

No. of Sample Tested

: 1 (One)

Customer Reference*

: Email Dated 22.03.2024

Proiect*

Not Furnished

Condition of Sample

: Satisfactory

Sample Drawn by

: Customer

Sample Identification*

'Epoxy floor Top Coat'

Grade/Type*

RACHTR FLOOR EP1010N * RACHTR

Brand* Period of Test

22.03.2024 to 29.03.2024

Mechanical Testing-(Building Materials)-Epoxy Grout

S.No.	Tests	Results	Test Method	
1.	Tensile Strength N/mm ² 7 Days	21.0	BS-6319 (P-7)	

Remark - mixing Ratio A:B:C (1:0.5:2.1)

****End of Report****





This page of the report is not under NABL accreditation

ione: 0821-2514972

ULR



सी एस आई आर - केन्द्रीय खाद्य प्रौद्योगिक अनुसंधान संस्थान, मैसूर - 570 020

CSIR-Central Food Technological Research Institute Mysore - 570 020, INDIA



TEST REPORT

5 2 5 3 1 8 0 0 0

CETRI CUSTOMER SERVICE CELL

Name & Address of the Customer	:	M/s. RachTR Chemicals Pvt. Ltd. 2/50 First Floor, Near DSIDC Complex, WHS Kiriti Nagar, New Delhi, West Delhi, Delhi- 110015	
Request Reference	:	Your letter dated: Nil	Page 1 of 1
Name of the Product/Sample [@]	:	Epoxy based coating- (RachTR Floor 1010 N)	

17.01.2019
SAMPLE NOT DRAWN BY US

Parameter / Simulant	Amount of Extractives	Limits as per USFDA – 175.300	Test Method	
(Temp/ Time)	mg/in ²	mg/in ²		
Overall Migration Test with Distilled Water (49°C/24 hrs.)	0.10	1.8 for single use 18 for repeated use	USFDA – 175.300 1 st April 2017	

SV : SA = 0.92 : 1

Sample Receipt Date

<u>Conclusion:</u> The values are below the limits specified as per USFDA 175.300, 1st April 2017, for intended use for contact with aqueous (water) foods/beverages for repeated use at room temperature filling and storing.

[®]Information as given by the customer.

Please Note: The results contained in this Test Report relate only to the sample tested. This Report is intended only for your guidance and not valid for legal purposes or for advertisement.

Food Safety & Analytical
Quality Control Laboratory
CFTRI, MYSORE